



INTEGRAL WATER RESISTANT PLASTICISER

Plasticity Improver For Mortar & Render

Technical Data Sheet



BUILDERS COMPLETE RANGE

**CLASS
EN934-3 T2**

Description:

A premium grade, high strength integral water resistant plasticiser designed to improve resistance to water penetration both internally and externally whilst giving all the benefits of a mortar plasticiser. Conforms to EN934-3:2009 + A1 (2012), Class T2.

Features & Benefits:

- ◆ Improves the plasticity of the mix making it easier to use.
- ◆ Improves water resistance.
- ◆ Retards suction in multi-layer renders.
- ◆ Reacts with free lime in the mortar to form hydrophobic crystals which block the pores, thereby improving the water resistance of the mix.
- ◆ Simply add to gauging water.

Uses

To help mortars and renders resist external and/or internal water pressures. Suitable for use on renderings, retaining walls, tanks, swimming pools, roof screeds, reservoirs, basement walls and all applications where water penetration is a problem.

Limitations

This is not a vapour-proofing product, therefore, a separate vapour-proof membrane is required for vapour-proof applications. Do not overmix the mortar/concrete, to prevent excessive air entrainment and subsequent loss of strength. Do not use at temperatures below +2°C or when temperature is expected to drop below 0°C within 24 hours.

Application

Shake well before use. Add to gauging water in the ratio of 0.25 - 0.5 litres Bond It INTEGRAL WATER RESISTANT PLASTICISER to each 25Kg bag of cement and reduce the total volume of gauging water to achieve the desired consistency. Use the appropriate sand/cement ratio for dense high quality mortar. Ensure the mortar is firmly compacted and do not over mix the mortar.

Size

5L and 25L plastic bottles. 200L also available on request.

Coverage

0.25 - 0.5 litres for every 25Kgs of cement.

Colour

Available in pink or green liquid.

Shelf Life

24 months from date of manufacture when stored in original, unopened bottles.

Storage Conditions

Store in cool, dry conditions in a sealed container between +5 and +30°C and protect from frost, high temperatures and sunlight.

Disposal Of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Remove any bottles or used material to a central disposal point in accordance with local regulations.

Health & Safety

Please refer to separate safety data sheet (SDS) for full handling, use and storage instructions. Keep out of reach of children. It is the user's responsibility to determine suitability for use. If in doubt, contact our Technical Department for advice.

Note: this information is for general guidance only, since site conditions and labour are beyond our control.



Specification Summary

Appearance	Pale pink or pale green liquid
Flammability	Non-flammable
Boiling Point	+100°C
Composition	Blend of fatty acids and potassium hydroxide
Solubility in water	Soluble
pH	12-14
Application Temperature	+2°C to +30°C
Commodity Code	3824400000

Product / Order Details

Code	Colour	Fill	Barcode	UFI
BDH020	Pink	5L	5060021361165	T410-FONR-T003-0MX6
BDH021	Pink	25L	5060021361172	T410-FONR-T003-0MX6
BDH022	Pink	200L	5060021364210	T410-FONR-T003-0MX6
BDH200	Green	5L	5060021362452	T410-FONR-T003-0MX6
BDH201	Green	25L	5060021362469	T410-FONR-T003-0MX6
BDH202	Green	200L	5060021362476	T410-FONR-T003-0MX6



Part of the Bond It Builders Complete Range

Head Office: Unit H4, Premier Way, Lowfields Business Park, Elland, West Yorkshire. HX5 9HF.
Telephone: +44 (0)1422 315300 **Email:** salesuk@bonditgroup.com
EU Office: SISL (Bond It) Ireland Limited, 70 Sir John Rogerson's Quay, Dublin 2. **Tel:** +353 1 960 9411
Website: www.bonditgroup.com

**UK
CA**

22

CE

13

BOND IT

H4 Premier Way, Elland. HX5 9HF. UK

EN934-3:2009

Air entraining plasticiser for masonry mortar EN934-3 T2.

DoP: BDH020-2/200-2 DoP: BDH020-2/200-2
NB: 0120 NB: 1029

Maximum chloride ion content <0.1% by mass

Maximum alkali content <1.5% by mass

Corrosive behaviour Contains components only from EN934-1:2008 Annex A.1

Note: The data presented in this leaflet is in accordance with the present state of our knowledge, but does not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the products for a particular purpose.



Version 5: Updated 11/06/24
 Supercedes: V4 13/10/22



Certificate Number 6152
 ISO 9001
 ISO 14001
 ISO 45001

bond it

An **ASTRAL** Limited Company